

AMENDMENT NO. 1 OCTOBER 2023
TO
IS 3456 : 2022 METHOD FOR DETERMINATION OF WATER-SOLUBLE MATTER
OF TEXTILE MATERIALS
(First Revision)

(Page 2, clause 8.3) — Substitute the following for the existing:

‘**8.3** Calculate the water-soluble matter as a percentage of the conditioned weight of the specimen by the following formula:

$$P = \frac{W_2}{W_1} \times 100$$

where

P = percentage of water-soluble matter;

W_2 = weight, in g, of the residue (*see 8.2*); and

W_1 = weight, in g, of the conditioned test specimen (*see 8.1*).’